## Progress in the Development of High Performance Pnictide Wires

<u>Xianping Zhang</u><sup>1</sup>, Chao Yao<sup>1</sup>, He Huang<sup>1</sup>, Chiheng Dong<sup>1</sup>, Satoshi Awaji<sup>2</sup>, and Yanwei Ma<sup>1</sup>

<sup>1</sup> Key Laboratory of Applied Superconductivity, Institute of Electrical Engineering, Chinese Academy of Sciences, PO Box 2703, Beijing 100190, China

<sup>2</sup> High Field Laboratory for Superconducting Materials, Institute for Materials Research, Tohoku University, Sendai 980-8577, Japan

## E-mail: zxp@mail.iee.ac.cn

Abstract— Iron pnictide superconductors are very attractive for applications in the high magnetic field region, because of their large upper critical field, small anisotropy, etc. However, the practical realization requires pnictide wires with high excellent transport currents and mechanical properties, which are multi-filamentary and homogeneous in long lengths, to be produced at low cost. A lot of works had been carried out to solve the problems associated with these factors. Recently, we have made further improvement in the high-field  $J_c$  of 122 type pnictide wires, which exhibited a transport critical current density value  $J_c$  as high as 5×10<sup>4</sup> A/cm<sup>2</sup> at 26 T, 4.2 K. The high density nano-scale defects formed in the superconducting core possibly account for this large in-field J<sub>c</sub>. We also get new results for the Cu-sheathed pnictide wires. By using a low temperature sintering process, the Cu-sheathed Sr122 samples exhibit a high  $J_c$  of  $3.5 \times 10^4$  A/cm<sup>2</sup> in 10 T and 1.6×10<sup>4</sup> A/cm<sup>2</sup> in 26 T at 4.2 K, respectively. This fascinating result indicates a promising future for Cu using as the sheath material in pnictide wires. At the same time, wires with a good mechanical property have been fabricated using Fe/Ag as composite sheath material in Sr122 wires. The composite sheath provides both inert reaction with the superconducting core and high mechanical properties of the wires. It is expected that further optimized properties in pnictide wires can be obtained based on improved manufacturing technologies.

## *Keywords (Index Terms)*– Pnictide superconductor, wires, critical current density.

IEEE/CSC & ESAS SUPERCONDUCTIVITY NEWS FORUM (global edition), No. 42, October 2017. Received October 20; Selected October 22, 2017. Reference STP599; Category 5. This invited presentation M40rB-02 was given at CEC-ICMC 2017, July 09-13, 2017, Madison (USA).