## Influence of Post-growth Thermal Treatments on the Critical Current Density of TSMG YBCO Bulk Superconductors

P. Diko<sup>1</sup>, V. Antal<sup>1</sup>, K. Zmorayová<sup>1</sup>, M. Šefčiková<sup>1</sup>, X. Chaud<sup>2</sup>, J. Kováč<sup>1</sup>, X. Yao<sup>3</sup>, X. Chen<sup>4</sup>, M. Eisterer<sup>5</sup> and H. W. Weber<sup>5</sup>

 <sup>1</sup>Institute of Experimental Physics SAS, Watsonova 47, 04001 Košice, Slovakia
<sup>2</sup>CNRS/CRETA, 25, Avenue des Martyrs, 38042 Grenoble Cedex 9, France
<sup>3</sup>Department of Physics, Shanghai Jiao Tong University, 800 Dongchuan Road, Shanghai 200240, People's Republic of China
<sup>4</sup>Department of Materials Science and Engineering, National Cheng Kung University (NCKU) Tainan, Taiwan
<sup>5</sup>Vienna University of Technology, Atominstitut, Stadionallee 2, 1020 Vienna, Austria

*Abstract* - Oxygenation and thermochemical post-growth treatments of top seeded melt-growth (TSMG) YBCO bulk superconductors can significantly influence critical current density. It is shown that, depending on oxygenation conditions and the size of 211 particles, different reductions of intrinsic critical current density values can be obtained due to the reduction in the sample cross-section caused by the presence of *a/b*-microcracks induced by 211 particles, and *a/b*-and *a/c*-cracks induced by oxygenation. The possibility of eliminating oxygenation cracks by high pressure oxygenation and consequently significantly increasing the macroscopic critical current density is demonstrated. An effective dopant concentration for chemical pinning is proposed and possible clustering of substitutions in the Y123 lattice by thermochemical treatments is shown.

IEEE/CSC & ESAS European Superconductivity News Forum (ESNF), No. 15, January 2010 Published in *Supercond. Sci. Technol.* (SuST) 23 (2010) 124002 (7pp)